



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-43-211-6144

FAX 82-43-211-6148

Report No : TAK-2020-036599

Receipt Date : 2020.03.02.

Representative : YOO JUNG SEUK

Test Completion Date : 2020.03.23.

Company name : HYUNDAI L&C

Address : 26, Eulji-ro 5-gil, Jung-gu, Seoul, Republic Korea

Sample name : HANEX(D)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Specific Gravity((23/23) °C)(Method A)	-	-	1.73	ASTM D792-13
Rockwell Hardness(HRM)(Procedure A)	-	-	87	ASTM D785-08(2015)
Tensile Strength(*)	MPa	-	32.8	ASTM D638-14
Tensile Modulus of Elasticity(*)	GPa	-	10.0	ASTM D638-14
Flexural Strength(**)	MPa	-	59.4	ASTM D790-17
Flexural Modulus of Elasticity(**)	GPa	-	9.67	ASTM D790-17
Izod Impact Strength(Method A)	J/m	-	15	ASTM D256-10(2018)
Water Absorption(24 h Immersion)	%	-	0.03	ASTM D570-98(2018)
Density(23 °C)(Method A)	g/cm ³	-	1.73	ASTM D792-13
Heat Resistance(Appearance)	-	-	No Defects	Referencing JIS K 6902 : 2007(Method B)
Heat Water Resistance(Appearance)	-	-	No Defects	Referencing JIS K 6902 : 2007(Method B)
Deflection Temperature Under Load(1.82 MPa)	°C	-	107	ASTM D648-18(Method B)
Thermal Expansion	1/°C	-	4.1 × 10 ⁻⁵	Referencing KS M 3015 : 2003

* Specimen: Type III, Speed of Testing: 5 mm/min(Modulus: 1 mm/min)

** Support Span: 190 mm, Speed of Testing: 5.0 mm/min

- Usage of Report : QUALITY CONTROL

- Next Page -

Cho Hyeong-gil

Prepared by Cho Hyeong-gil

Tel : 02-2092-3698

You Seok

Reviewed by You Seok

Tel : 1577-0091(ARS ①-④)

2020.03.23

Korea Testing & Research Institute

President



QR Code for forgery

Page : 1 of 2

전자문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-43-211-6144

FAX 82-43-211-6148

Report No : TAK-2020-036599

Receipt Date : 2020.03.02.

Representative : YOO JUNG SEUK

Test Completion Date : 2020.03.23.

Company name : HYUNDAI L&C

Address : 26, Eulji-ro 5-gil, Jung-gu, Seoul, Republic Korea

Sample name : HANEX(D)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

- Note :
1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Cho Hyeong-gil

Prepared by Cho Hyeong-gil

Tel : 02-2092-3698

You Seok

Reviewed by You Seok

Tel : 1577-0091(ARS ①→④)

2020.03.23

Korea Testing & Research Institute

President



QR Code for forgery